

TECHGUARD 101

EPOXY- POLYAMIDE ZINC RICH PRIMER

DESCRIPTION

TECHGUARD 101 is a two component organic zinc rich primer, which provides optimal galvanic protection for steel surfaces exposed to corrosive environments. This effective action is derived from the galvanic couplers formed between the zinc coating and the metal substrate. This protection exists even if the primer is scratched or gouged.

TECHNICAL INFORMATION

CHARACTERISTICS	VALUE
Color	Zinc Grey
Generic Type	Epoxy- Polyamide
Pigment Type	Metallic Zinc Dust
Volume solids (Mixed)	37%
Theoretical Coverage	40 sq. ft. /ltr.
Film Thickness Dry	40μ
Dry Time @ 70°F	
To touch	4.0 Hrs.
To recoat	16 Hrs.
Dries By	Chemical Cure
Dry Heat Resistance	350°F
Viscosity (Mixed)	25+/- 5sec by F/C 4
Flash Point	84°F
Application	Surface must be dry and above 5°above the dew point
Reduction	Brush do not Thin Roller do not Thin Spray do not Thin
Clean Up Thinner	Xylene
Mixing Ratio	100 : 20 by wt.
Induction time	30 Min.
Pot Life@70°F	2-3 Hrs. weight per Ltr (mixed)
Storage temperature	Min. 40°F Max. 100°F

FEATURES / ADVANTAGES

- Dry film contains 80% of zinc dust.
- Provides optimal galvanic protection for steel, excellent chemical resistant base for high performance topcoats.
- Protects metal substrate exposed to corrosive environments.

TECHGUARD 101

EPOXY- POLYAMIDE ZINC RICH PRIMER

DIRECTION FOR USE

BARE STEEL

All surfaces shall be free of rust, mill scale, and contaminants such as oil, grease, dirt, and salts. Before any surface preparation is attempted, oil and grease must be removed by employing SSPC- SP1 solvent cleaning. For large areas, use oil and grease emulsifier.

FOR BEST PERFORMANCE

Use commercial blast cleaning to SSPC- SP6 to remove mill scale, rust and other contaminants and leave a roughened surface.

Use power tool cleaning to bare metal SSPC- SP11 to remove mill scale, rust and other contaminants and leave a roughened surface.

APPLICATION INFORMATION

Generally, Techguard 101 is best applied by a spray. Due to the rapid drying of this coating only small areas may be coated by a brush applicator pad or a roller must be taken to achieve the specified wet and dry thickness so that even & uniform coats are obtained.

APPLICATION EQUIPMENT

- DeVilbiss or Equivalent Equipment
- Air spray: MBC 510 Gun (stainless steel) "E" tip and fluid needle, 64 or 765 Air Cup, Mastic Spring, Teflon
- Packing: Maximum of 5 ft. 5/16" (7.94 MM) I.D. Air and 1/2" (12.70 MM) I.D. Fluid Hose
- Atomization Pressure: 50 PSI, Fluid Pressure: 15 PSI.
- Airless Spray: Utilize only equipment recommended by the manufacturer as being suitable for application of zinc rich Products. Continuous agitation of mixed material is required during application.

Equipment's must be capable of maintaining 1500 PSI at the tip. Hose length in excess of 25 ft. and work at heights greater than 10 ft. above the pump are to be avoided. These conditions promote zinc setting in the fluid hose with resulting top plugging and non uniform distribution of zinc in the applied film.

REPAIR OF DAMAGED SPOTS

This product is also recommended for field touch up of shop applied inorganic zinc primer prior to application of high performance topcoats.

TECHGUARD 101

EPOXY- POLYAMIDE ZINC RICH PRIMER

PACKING

4 liters and 20 liters containers

PRECAUTION

DANGER! FLAMMABLE! Contains xylene! Keep away from heat, sparks and flame. Avoid breathing the vapour. Use with forced air ventilation in confined areas. Avoid contact of resin or hardener with skin or eyes. In case of eye contact, flush immediately with plenty of water and consult a physician. Do not take internally.

- Not to be applied when air and surface temperatures are below 50°F
- Must be top coated with appropriate coating when used in corrosive environments
- Caution when opening containers- gassing may occur
- Not for immersion or for exposure to acids & alkalis without proper topcoats.